

CLASSIC GLOSS & CLASSIC PEARL PAPER



ILFORD GALERIE Classic Paper is a premium RC paper designed to provide images with excellent colour stability and an elegant professional finish, from today's range of photo-dedicated dye desktop inkjet printers.

ILFORD GALERIE Classic Paper is available in "Gloss" and "Pearl" finish.

Note : this product is not compatible with printers using pigment inks.

TIPS

- The glossy side (or the pearl side) of the paper is the printing surface.
- Follow the printer manufacturer's instructions for loading the paper.
- Store the paper in the original packaging to prevent damage to the printing surface.
- The paper can be handled immediately after printing; however, it should be fully dried prior to storing or stacking.

AVOID...

- ... touching the printing surface of the paper, this may affect image and colour quality.
- ... exposing the paper to extreme temperature and humidity as this can reduce image quality.

PRINTER SETTINGS GUIDELINES

This paper is designed for use in quality inkjet printers including Epson®, Hewlett Packard®, Canon®, Lexmark® and other leading brands.

- Best results are achieved with printers designed for photo quality.
- Use "Generic Printer" settings if your printer is not listed in the PRINTER SETTINGS GUIDE (see separate download).
- Personal preferences and individual printing conditions can vary. For best results, printer settings may need to be changed. Experiment with different settings to achieve the preferred look for your prints.

TIPS ON PRINTER SOFTWARE

- Changing the media type (i.e. paper, film, etc.) under printer options alters the look of the print and can affect colour quality.
- Red, Green, Blue (RGB) files process differently than Cyan, Magenta, Yellow, Black (CMYK) files. Most images yield higher print quality when printed from RGB files.

PHYSICAL PROPERTIES (target values)

	GLOSS	PEARL
Weight	240 g/m ²	240 g/m ²
Opacity	99 %	99 %
Caliper	230 micron	250 micron
Tint (Lab)	95.5, 0.5, -4.0	94.5, 1.0, -4.7
Gloss	50-80 % (20°)	14-22 % (60°)

ILFORD

GALERIE

CLASSIC GLOSS & PEARL PAPER IGCGP9/IGCPP9

ILFORD GALERIE CLASSIC PAPER is a premium polymer RC paper designed to provide images with excellent colour stability and an elegant professional finish, from today's range of photo-dedicated desktop inkjet printers.

FEATURES

- Classic gloss / pearl finish
- True feel of a real photograph
- Excellent image stability
- Superb photographic image quality and consistency
- Designed for high speed printers
- Excellent compatibility with all high quality inkjet printers, especially those designed for photo output
- Good archival properties and fade resistance (see Note below)

PRINTER & INK COMPATIBILITY

Compatible with most photo-dedicated and photo-capable desktop printers and the corresponding vendor's inks.

Not compatible with pigment inks.

AVAILABILITY

A4 (210x297mm) / U4 (8.5"x11")	25 sheets, 100 sheets – 250 sheets (USA only)
A3 (297x420mm) / U3 (11"x17")	25 sheets
A3+ (329x483mm) / U3+ (13"x19")	25 sheets

PHYSICAL PROPERTIES (TARGET VALUES)

	GLOSS	PEARL
Weight	240g/m ²	250g/m ²
Opacity	99%	99%
Caliper	230micron	250micron
Tint (Lab)	95.5, 0.5, -4.0	94.5, 1.0, -4.7
Gloss (60°)	50-80% (20°)	14-22% (60°)

NOTE

ILFORD GALERIE CLASSIC PAPER has similar resistance to air pollutants as conventional photographic print media. Compared to the "instant dry" inkjet media it does not suffer from "gas fading" issues under similar conditions, and can also be kept in both light and dark storage without protection from laminates, sleeves or glass. In an unprotected display, indoors and away from direct sunlight, life expectancy of up to 20 years can be expected depending on the ink used.

The life expectancy of all inkjet media is influenced by humidity, light and the ink being used. At higher light levels or humidity, one should expect a shorter life expectancy than at low light level or humidity. Some inkjet printer inks also offer poor stability when compared with others. When storing and handling prints at the extremes of the environmental range (<10% r.h. and >70%), performance and permanence may be reduced.

Specifications subject to change without notice.